

All Dielectric Self-Supporting Cable




KABELOVNA Děčín Podmokly s.r.o.
 Ústecká 840/33, 405 33 Děčín 5
 Czech Republic
 DIČ CZ26759993
 tel.: +420 412 706 222
 www.kabelovna.cz

ID: **N6XI**

24.1.2019 ver. 7

ADSS-DQ(ZN)2YT 3kN 12×2,5 max. 144F

This cable is suitable for outdoor aerial use.



Mechanical and Environmental properties

Test	Value	Unit	Method
Cable outer diameter	16,4±0,4	mm	EN 60811-203
Cable weight	203	kg/km	
Outer jacket thickness	1,8	mm	
Loose tube diameter	2,5	mm	
Thermal expansion coefficient	24,2	ppm/K	
Modulus of elasticity	6,1	Gpa	
Max. allowable tension	3	kN	EN 60794-1-21-E1
Max. operation tension	2,6	kN	EN 60794-1-21-E3
Crush resistance test	3000	N	EN 60794-1-21-E4
Impact resistance test	30	Number of impact	
Min. bend radius (no load)	15	× OD	EN 60794-1-21-E11a
Min. bend radius (load)	20	× OD	EN 60794-1-21-E11b
Temperature range	Installation	-15 to +50	°C
	Operation	-40 to +70	°C
	Storage	-40 to +70	°C

Cable life time - minimum 30 years

Sheat Marking

Print colour	White
Print method	INK-Jet or Hot-foil
Print legend	Manufacturer's name, job number, type of cable, length marking @ 1 m intervals

Other print legends available on request

Fibre colour coding

According to IEC 60304

1	Red	7	Brown
2	Green	8	Violet
3	Blue	9	Turquoise
4	Yellow	10	Black
5	White	11	Orange
6	Grey	12	Pink

Other fibre colour sequences available on request

Tube colour coding

1	Red
2	Green
3-12	White

in the case of lower number of fibres some tubes are replaced by uncoloured fillers

Other tubes colour sequences available on request

Packing

Depending on ordered put-up lengths

All Dielectric Self-Supporting Cable



KABELOVNA Děčín Podmokly s.r.o.
 Ústecká 840/33, 405 33 Děčín 5
 Czech Republic
 DIČ CZ26759993
 tel.: +420 412 706 222
 www.kabelovna.cz

ID: **N6XI**

24.1.2019 ver. 7

ADSS-DQ(ZN)2YT 3kN 12×2,5 max. 144F

SPAN (m)	INSTALATION		NESC LIGHT			NESC MEDIUM			NESC HEAVY		
			sag (m)		load (N)	Sag (m)		load (N)	sag (m)		load (N)
	Sag 1,5%(m)	N	horizontal	vertical		horizontal	vertical		horizontal	vertical	
40	0,6	685	1,06	0,35	1573	0,72	0,98	1812	0,72	1,32	2577
60	0,9	1027	1,74	0,58	2168	1,19	1,62	2478			
80	1,2	1370	2,47	0,82	2716						

